Asahi Kasei Chemicals Corporation - Polyamide 66

Friday, February 26, 2016

General Information						
General						
Material Status	Commercial: Active					
Availability	 Africa & Middle East Asia Pacific	 Europe North America				
Features	Good Flow	Good Stiffness	Good Toughness			
Uses	Automotive ApplicationsConnectors	Consumer ApplicationsFittings				

ASTM & ISO Properties ¹								
Physical	Dry	Conditioned	Unit	Test Method				
Specific Gravity	1.14		g/cm³	ASTM D792 ISO 1183				
Molding Shrinkage - Flow	1.3 to 2.0		%	Internal Method				
Water Absorption								
Saturation, 23°C		2.5	%					
Equilibrium, 23°C, 50% RH		2.5	%	ISO 62				
Mechanical	Dry	Conditioned	Unit	Test Method				
Tensile Modulus (23°C)	3000	1200	MPa	ISO 527-2				
Tensile Stress								
Yield, 23°C	82.0	52.0	MPa	ISO 527-2				
	79.0	57.0	MPa	ASTM D638				
Tensile Strain								
Yield, 23°C	4.0	24	%	ISO 527-2				
Break	50	250	%	ASTM D638				
Break, 23°C		> 100	%	ISO 527-2				
Flexural Modulus								
	2800	1200	MPa	ASTM D790				
23°C	2700	1100	MPa	ISO 178				
Flexural Strength								
	118	54.0	MPa	ASTM D790				
23°C	113	42.0	MPa	ISO 178				
Taber Abrasion Resistance				ASTM D1044				
1000 Cycles		7.00	mg					
mpact	Dry	Conditioned	Unit	Test Method				
Charpy Notched Impact Strength	6.0	15	kJ/m²	ISO 179				
Charpy Unnotched Impact Strength	No Break	No Break		ISO 179				
Notched Izod Impact	39	150	J/m	ASTM D256				
Hardness	Dry	Conditioned	Unit	Test Method				
Rockwell Hardness				ASTM D785				
M-Scale	80	55		ISO 2039-2				
R-Scale	120	108						

Disclaimer:

 Orally-related application : any part, device or component which may come into direct oral contact or into direct contact with drinking foods or beverages.
For drinking water application, please consult Asahi Ksei Chemicals Corporation.
Medically-related applications : any part, or component which may be used intracorporeally or which may in dialysis or other processes come into direct or indirect contact with body tissue , body fluids , or transfusion fluids.

⁻ Data shown are typical values obtained by proper testing methods and shoud not be used for specification purpose.

Please use these data for selecting the most appropriate grade suitable for specific usage. These data may be changed because of improvement in properties. - Be sure to read the relevant SDS before handling and use, and always follow the Important Precautions.

⁻ Do not use plastics in any of the following orally-or medically-related applications.

Leona[™] 1300S Asahi Kasei Chemicals Corporation - Polyamide 66

Thermal	Dry	Conditioned	Unit	Test Method
Deflection Temperature Under Load				
0.45 MPa, Unannealed	230		°C	ASTM D648
0.45 MPa, Unannealed	190		°C	ISO 75-2/B
1.8 MPa, Unannealed	70.0		°C	ASTM D648 ISO 75-2/A
CLTE - Flow	8.0E-5		cm/cm/°C	ASTM D696
Specific Heat	1670		J/kg/°C	
Thermal Conductivity	0.20		W/m/K	
Electrical	Dry	Conditioned	Unit	Test Method
Surface Resistivity	1.0E+13		ohms	ASTM D257 IEC 60093
Volume Resistivity				
	1.0E+14		ohms∙cm	ASTM D257
23°C	1.0E+14		ohms∙cm	IEC 60093
Dielectric Strength	20		kV/mm	ASTM D149 IEC 60243-1
Comparative Tracking Index				IEC 60112
3.00 mm	600		V	
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating (0.750 mm)	V-2			UL 94
Glow Wire Flammability Index				IEC 60695-2-12
3.00 mm	960		°C	
Oxygen Index	26		%	ASTM D2863

Notes

¹ Typical properties: these are not to be construed as specifications.

Disclaimer:

⁻ Data shown are typical values obtained by proper testing methods and shoud not be used for specification purpose.

Please use these data for selecting the most appropriate grade suitable for specific usage. These data may be changed because of improvement in properties. - Be sure to read the relevant SDS before handling and use, and always follow the Important Precautions.

⁻ Do not use plastics in any of the following orally-or medically-related applications. Orally-related application : any part, device or component which may come into direct oral contact or into direct contact with drinking foods or beverages.
For drinking water application, please consult Asahi Ksei Chemicals Corporation.
Medically-related applications : any part, or component which may be used intracorporeally or which may in dialysis or other processes come into direct or indirect or indirect with body tissue , body fluids ,

or transfusion fluids.