

Flame Retardant ABS POLYLAC® PA-764

Product Description: F.R. Weather resistant

Properties	ISO Test Method	Test Condition	Unit	PA-764
Melt Flow Index	1133	220°C×10KG	ml/10 min	28
Mass Density	1183	23 °C	g/cm ³	1.19
Tensile Strength	527	50 mm/min, yield	MPa	36
		50 mm/min, break	MPa	27
Tensile Elongation	527	50 mm/min	%	10
Flexural Strength	178	2 mm/min	MPa	55
Flexural Modulus		2 mm/min	GPa	1.7
Izod Impact Strength	180/1A	23°C, Notched	KJ/m ²	13
		-30°C, Notched	KJ/m ²	7
Charpy Impact Strength	179	23 °C Notched	KJ/m ²	13
		-30 °C Notched	KJ/m ²	7
Vicat Softening Temp.	306	1 Kg,50 °C/hr	°C	101
		5 Kg,50 °C/hr	°C	90
Heat Distortion Temp.	75/A	1.8 MPa Unannealed	°C	82
		1.8 MPa Annealed	°C	92
Coefficient of Linear Thermal Expansion	11359	-	-	8.46 x 10 ⁻⁵
Flammability	-	UL-94	-	1.5mm V-0 1.5mm 5VB 2.5mm 5VA
Mold Shrinkage	294-4	-	%	0.3~0.6
Symbol	1043	-	-	>ABS-FR(17)<

October 8, 2020

Notes : These are typical properties only and are not to be construed as specifications. Users should confirm results by their own test

The above statement is based on our current level of knowledge and covers the above products directly manufactured and supplied by CHI MEI CORPORATION at the date of issue. CHI MEI CORPORATION makes no warranties, whether express or implied, and assumes no liability in connection with any use of above information. Notwithstanding the foregoing, CHI MEI CORPORATION shall in no event be held obligated or liable for any claims due to or arising from (i) any customer provided, consigned, materials and/or parts, which are incorporated or adopted in the products; (ii) any combination of the products with material not provided or authorized by our company; (iii) any modifications to the products which are made or directed by customer; (iv) our compliance with the specifications, instructions, and/or designs provided by customer; (v) any anti-trust, unfair competition and/or other unlawful actions effected by customer; or (vi) any defects, infringement, breach and/or violation which are arising out of customer's faults or otherwise not solely and directly attributable to CHI MEI CORPORATION. In no event will CHI MEI CORPORATION be liable for any indirect, special, exemplary, punitive, or consequential damages (including lost profits) of any nature whatsoever whether arising out of the purchase, shipment, unloading, handling, or use of any product or otherwise.