

Oil-extended TPE KIBITON® Characteristics PB-587

| 特性 PROPERTIES | 測試方法 TEST METHOD | 測試條件 TEST CONDITION | 單位 UNIT | 加油膠 OIL-EXTENDED |
|-------------------------|---------------------|------------------------|------------|---------------------|
| | | | | PB-587 |
| 丁二烯/苯乙烯比例 BD/SM | ASTM D5775 | - | % | 45/55 |
| 揮發份 Volatile matter | ASTM D5668 | - | wt% | 0.6 |
| 灰份 Ash Content | ASTM D5667 | - | wt% | 0.3 |
| 加工含油量 Oil Content | ASTM D5774 | - | wt% | 28.5 |
| 熔融指數 Melt Flow Index | ASTM D1238 | 190 °C, 5 Kg | g/10 min | 12 |
| 硬度 Hardness | ASTM D2240 | - | Shore-A | 92 |
| 比重 Specific Gravity | ASTM D792 | 23 °C | - | 0.94 |

September 7, 2021

Notes : These are typical properties only and are not to be construed as specifications. Users should confirm results by their own tests.

The above statement is based on our current level of knowledge and covers the above products directly manufactured and supplied by CHIMEI CORPORATION at the date of issue. CHIMEI CORPORATION makes no warranties, whether express or implied, and assumes no liability in connection with any use of above information. Notwithstanding the foregoing, CHIMEI CORPORATION shall in no event be held obligated or liable for any claims due to or arising from (i) any customer provided, consigned, materials and/or parts, which are incorporated or adopted in the products; (ii) any combination of the products with material not provided or authorized by our company; (iii) any modifications to the products which are made or directed by customer; (iv) our compliance with the specifications, instructions, and/or designs provided by customer; (v) any anti-trust, unfair competition and/or other unlawful actions effected by customer; or (vi) any defects, infringement, breach and/or violation which are arising out of customer's faults or otherwise not solely and directly attributable to CHIMEI CORPORATION. In no event will CHIMEI CORPORATION be liable for any indirect, special, exemplary, punitive, or consequential damages (including lost profits) of any nature whatsoever whether arising out of the purchase, shipment, unloading, handling, or use of any product or otherwise.