

General Q resin KIBITON® Characteristics PB-5903

特性 PROPERTIES	測試方法 ISO TEST METHOD	測試條件 TEST CONDITION	單位 UNIT	一般級 GENERAL
				PB-5903
熔體流動速率 MVR	1133	200 °C, 5 Kg	g/10 min	10
質量密度 Mass Density	1183	23 °C	g/cm ³	1.01
拉伸強度 Tensile Strength	527	50mm/min,yield;4mm	MPa	27
		50mm/min,break;4mm	MPa	19
延伸率 Tensile Elongation	527	50mm/min,yield;4mm	%	2
		50mm/min,break;4mm	%	199
彎曲強度 Flexural Strength	178	2mm/min;4mm	MPa	36
彎曲彈性模數 Flexural Modulus	178	2mm/min;4mm	MPa	1400
IZOD 衝擊強度 Izod Impact	180/1A	23°C, Notched	KJ/m ²	3.0
		-30°C, Notched	KJ/m ²	-
Charpy 衝擊強度 Charpy Impact	179	23°C, Notched	KJ/m ²	2.8
		-30°C, Notched	KJ/m ²	-
		23°C, Notched	KJ/m ²	72
		-30°C, Notched	KJ/m ²	-
維氏軟化溫度 Vicat Softening Temp.	306	50°C/hr,1KG,4mm	°C	86
		50°C/hr,5KG,4mm	°C	64
熱變形溫度 Heat Distortion Temp.	75/A	1.86Kg,4mm,unannealed	°C	66
		1.86Kg,4mm,annealed	°C	75

September 7, 2021

Notes : These are typical properties only and are not to be construed as specifications. Users should confirm results by their own tests.

The above statement is based on our current level of knowledge and covers the above products directly manufactured and supplied by CHIMEI CORPORATION at the date of issue. CHIMEI CORPORATION makes no warranties, whether express or implied, and assumes no liability in connection with any use of above information. Notwithstanding the foregoing, CHIMEI CORPORATION shall in no event be held obligated or liable for any claims due to or arising from (i) any customer provided, consigned, materials and/or parts, which are incorporated or adopted in the products; (ii) any combination of the products with material not provided or authorized by our company; (iii) any modifications to the products which are made or directed by customer; (iv) our compliance with the specifications, instructions, and/or designs provided by customer; (v) any anti-trust, unfair competition and/or other unlawful actions effected by customer; or (vi) any defects, infringement, breach and/or violation which are arising out of customer's faults or otherwise not solely and directly attributable to CHIMEI CORPORATION. In no event will CHIMEI CORPORATION be liable for any indirect, special, exemplary, punitive, or consequential damages (including lost profits) of any nature whatsoever whether arising out of the purchase, shipment, unloading, handling, or use of any product or otherwise.