

HBR KIBIPOL® Characteristics PR-040

特性 PROPERTIES	測試方法 TEST METHOD	測試條件 TEST CONDITION	單位 UNIT	高順式橡膠 HBR
				PR-040
慕尼指數 Mooney	ASTM D1646	-	MU	44±5
丁二烯/苯乙烯比例 BD/SM	ASTM D5775	-	%	100/0
揮發份 Volatile matter	ASTM D5668	-	wt%	≤0.50
灰份 Ash Content	ASTM D5667	-	wt%	≤0.50
比重 Specific Gravity	ASTM D792	23 °C	-	0.91
APHA 色澤 APHA color	ASTM D1209	-	APHA	≤10
Cis 含量 Cis Content	-	-	%	> 97
Vinyl 含量 Vinyl Content	-	-	%	< 1
包裝重量 Bale Weight	-	-	Kg	35
包裝膜 Wrapping film	-	-	Type	LDPE

September 7, 2021

Notes : These are typical properties only and are not to be construed as specifications. Users should confirm results by their own tests.

The above statement is based on our current level of knowledge and covers the above products directly manufactured and supplied by CHIMEI CORPORATION at the date of issue. CHIMEI CORPORATION makes no warranties, whether express or implied, and assumes no liability in connection with any use of above information. Notwithstanding the foregoing, CHIMEI CORPORATION shall in no event be held obligated or liable for any claims due to or arising from (i) any customer provided, consigned, materials and/or parts, which are incorporated or adopted in the products; (ii) any combination of the products with material not provided or authorized by our company; (iii) any modifications to the products which are made or directed by customer; (iv) our compliance with the specifications, instructions, and/or designs provided by customer; (v) any anti-trust, unfair competition and/or other unlawful actions effected by customer; or (vi) any defects, infringement, breach and/or violation which are arising out of customer's faults or otherwise not solely and directly attributable to CHIMEI CORPORATION. In no event will CHIMEI CORPORATION be liable for any indirect, special, exemplary, punitive, or consequential damages (including lost profits) of any nature whatsoever whether arising out of the purchase, shipment, unloading, handling, or use of any product or otherwise.